RAVATHERM™ XPS X 300 SB



Technical data sheet

Properties	Valu	ie		U	nit	Standard		EN13164 esignation Code	
Thermal Conductivity Declared		30	< 60mm	W/	m.K	EN 13164		λD	
	0.03	31	≥ 60mm	W/	m.K				
Compressive stress or compressive strength@ 10% deformation	n 300)		k	Ра	EN 826	(CS(10\Y)	
Compressive Creep max after 50 years < 2% deformation unde stress σC	r 130)		k	Ра	EN 1606	СС	(2/1.5/50)	
Water vapour diffusion resistance factor μ (tabulated value)	150)			-	EN 12086		MU	
Long term water absorption by total immersion	< 0.	7		%		EN 12087		WL(T)	
Water pick-up by diffusion	< 2	2	50 < 80mm	Omm %		EN 12088		WD(V)	
	< 1		≥ 80mm						
Water pick up after Freeze Thaw	< 1			(%	EN 12091		FTCD	
Dimensional stability under specified temperature (70°C) and humidity conditions (90%rh)	< 5	5		C	%	EN 1604	С	S(70,90)	
Deformation under specified compressive load (40kPa) and temperature (70°C) conditions	< 5	5		C	%	EN 1605		DLT(2)5	
Coefficient of linear thermal expansion (typical value)	0.0	7		mm/	(m.K)	-		-	
Fire Performance	Е			Euro	class	EN 13501-	1		
Temperature limits	-50/+	75		٥	С	-			
Thickness tolerances	1			CI	ass	EN 823		Т	
Dimensions Wic	th 600)		m	nm	EN 822			
Leng	th 250	0		mm		EN 822			
Edge Profile	Butt E	dge							
Surface finish	Ski	n							
Thermal resistance ¹									
Thickness(mm)	30	40	50	60	75	100	125	150	
R _d m².K/W	1.00	1.30	1.65	1.95	2.40	3.20	4.00	4.80	

Material shall be stored inside in original packaging, away from direct sun light or heat sources

Note: The information and data contained in this technical data sheet do not represent exact sales specifications. The features of the products mentioned may vary. The information contained in this document has been provided in good faith, however it does not imply any liability, guarantee or assurance of product performance. It is the purchaser's responsibility to determine whether these products are suitable for the application desired and to ensure that the site of work and method of application conform with current legislation. No license is hereby granted for the use of patents or other industrial or intellectual property rights. If products are purchased, we advise following the most up-to-date suggestions and recommendations.





¹⁾ Thickness dependant

¹ N/mm² = 10³ kPa = 1MPa